



DRY SHAKE CONCRETE FLOOR HARDENER FOR STAMPED CONCRETE

DESCRIPTION:

ROKSOSTAMPOCRETE is a premixed dry shake floor hardener applied over freshly laid concrete. It is formulated from selected graded aggregate, cement and special additives to provide a non-metallic, non-oxidizing, dense and smooth surface with high abrasion and wear resistance. **ROKSO STAMPOREL** is a premixed special hydrophobic releasing powder mixed with high quality pigments.

USES:

- Parking areas where there are dynamic and static loads
- Warehouses and godowns
- Side walk and footpath
- Garden landscaping

ADVANTAGES:

- Resistance to UV rays
- Good resistance to wearing and abrasion
- Easy to apply
- Provides monolithic floor
- Premixed, ready to use
- Available in wide range of colours
- Decorative finish as a finished stamped concrete floor

COMPLIANCE STANDARD :
EN 13813, Class CT-C35-F5-AR6

METHOD OF APPLICATION:

All formwork should be erected properly and the right time to spread the **ROKSO STAMPOCRETE** on concrete surface is when light foot traffic leaves an imprint of about 3 - 6 mm.

Any bleed water should be removed and the concrete surfaces should be floated using a wood or magnesium "Bull-float" prior to the application of the colour hardener "**ROKSO STAMPOCRETE**".

Spread two-thirds of the required quantity of **ROKSO STAMPOCRETE** on to the concrete surface and allow the material to absorb moisture from concrete.

The remaining quantity of **ROKSO STAMPOCRETE** is applied evenly on to the surface.

Using a trowel, the surface should be trowelled well to eliminate any float marks and to achieve the final finish. Prior to imprinting, the trowelled slab should be covered with powder release agent "**ROKSO STAMPOREL**" at a rate of 5 to 7 m²/kg.

Using a reference line, begin by placing the first mat using this line and move across the slab. When stamping, the mats should be tamped using a special pounder without delay.

The finished slab should be left for a minimum of 2–3 days to set. All excess powder release agent

“**ROKSO STAMPOREL**” should be brushed and clean with water.

The slab must be completely dry before the sealer coat is applied. The surface must be sealed using

ROKSO STAMPSEAL. The first coat should be applied at a rate of 6–10m²/ liter and second coat can be applied if required after the first coat has dried.

TECHNICAL INFORMATION:

Properties	Results
Appearance	Different colours
Maximum wear depth	0.6mm
Flexural strength	> 6 N/m m ²
Compressive strength	> 40N/m m ²

COVERAGE:

ROKSO STAMPOCRETE	3–5kg/m ² depending on colour
--------------------------	--

CLEANING:

All tools should be cleaned immediately after finishing with fresh water.

CURING:

Normal good curing practice should be adopted.

PACKAGING:

ROKSO STAMPOCRETE is available in 25kg bags.

HEALTH AND SAFETY:

Specific care and attention should be paid to handling, storage and spill response of this product. Skin contact should be avoided as the material is slightly acidic. Any splashes should be washed well with water. If contact with eyes occurs wash immediately with water and take medical advice.

Manufactured in INDIA by
ROKSO INDIA PRIVATE LIMITED

AN ISO 9001 : 2015 CERTIFIED COMPANY

ADMN.OFFICE: 605,SAI JANAK CLASSIC,ABOVE MURLIDHAR SWEETS, NEAR FLYOVER BRIDGE, DEVIDAS LANE, BORIVALI (W) MUMBAI-103
REGD OFFICE : 202,MADHUVAN,SHRI KRISHNA COMPLEX,NR.SHRIRAM NAGAR,VIVA COLLEGE RD,VIRAR(WEST) DI :PALGHAR -401303 MS
E-MAIL : info@roksoindia.com / WEB SITE : www.roksoindia.com

The data & guidelines provided hereabove is based on compiled information which we believe reliable. Users are requested to test all the applications independently before commercial use. This data & informations are non binding & we donot assure any liability for failure of any guidelines or performance of the product as correct identification of the problem, quality of the other materials & on-site workmanship are factors beyond our control.